



120 Valley Court
 Oak Ridge, TN 37830
 Ph: 865-482-5717
 FAX: 865-482-1281
 zypcoatings.com

BN Type M

A Moderate-loading Boron Nitride Releasecoat Of Near-neutral pH

BN Type M has been developed as a water-based coating with moderate loading of Boron Nitride (BN) that exhibits good paintability onto any substrates. BN Type M provides non-stick, non-wetting with molten aluminum and its alloys and drosses. The paint is not deteriorated by freezing.

BN Type M is ready-to-use or can be diluted with water if needed. When diluted, Type M is a relatively-soft, washcoat-type coating that prevents reactions/interactions/sticking with molten metal.

Key Attributes

- Consistency of coated parts release and lubrication of molds
- Provides nonwetting, non-stick, release, lubrication and all the properties of BN
- Can be used as is or diluted with water as desired.
- Water-based, safe and easy-to-clean-up
- Not deteriorated by freezing

Ideal Use

- Permanent Molds
- Low Pressure or Gravity Die casting

Use Notes

1. Resuspend if needed. Can dilute with water.
2. Clean surfaces to be painted of any oils dirt, scale, etc.
3. Apply 1-3 layers by brush or spray like ordinary house paint, drying after each layer
4. Allow to dry thoroughly at room temperature before use.

Safety Information

- Consult SDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



Specifications

Active Ingredient	BN
Max Use Temperature	Air 1832 F / 1000 C Vac 2552 F / 1400 C Inert 3272 F / 1800 C
Use Atmosphere	All
Fired Composition	>85% BN
Liquid Carrier	Water
Binder Phase	Magnesium Silicate
Active Ingredient Level	Medium Loading
Brookfield Viscosity (cps)	850-1175 @3/60
Specific Gravity	1.03
Color	Blue
Shelf Life (months)	>12
Coverage (ft ² /gal)	100 to 400
Coating pH	7-8
H F R Ratings	1-0-0
Substrate Use	All

Sizes and colors

BN Type M is a blue colored paint. Also available as white paint

Standard Size: wide-mouth 1 gallon pail or 5 gallon pail

CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use.

In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted. Teflon® - reg. trademark of DuPont.