



120 Valley Court
Oak Ridge, TN 37830
Ph: 865-482-5717
FAX: 865-482-1281
zypcoatings.com

Boron Nitride Lubriccoat® NFN-12

Nonflammable-solvent based paint utilizing <100 nanometer BN particles

ZYP Coating's Boron Nitride Lubriccoat NFN-12 is an easily applied, non-aqueous, nonflammable-solvent based coating. The coating contains very unique Boron Nitride that is less than 100 nanometers. BN Lubriccoat NFN-12 is usable to 1000 C (1832 F) in air.

Key Attributes

- Nonflammable-Solvent Based Paint
- Unique active ingredient Boron Nitride less than 100 nanometers
- Usable to 1000 C or higher in all atmospheres
- Applies like house paint

Ideal Use

- Reducing Friction
- Providing Release
- Barrier Layer

Use Notes

1. Resuspend if needed.
2. Clean surfaces to be painted of any oils dirt, scale, etc.
3. Apply one thin layer by brush, dip or air-spray. If using more layers, dry between them.
4. Dry thoroughly before use, at room temperature for about 90 minutes or, for faster drying, with a lab dryer or conventional hair dryer at around 60 C (140 F) for 5-15 minutes.

Safety Information

- Consult SDS before use.
- Avoid breathing of vapors.
- For Industrial use only.



Specifications

Active Ingredient	BN, <100 nm
Max Use Temperature	Air 1832 F / 1000 C Vac 2550 F / 1400 C Inert 3272 F / 1800 C
Use Atmosphere	All
Fired Composition (Air@800 C)	>94% BN
Liquid Carrier	Nonflammable solvent mix
Binder Phase	Magnesium Silicate
Brookfield Viscosity (cps)	<66 @2/60
Specific Gravity	1.2
Color	White
Shelf Life (months)	>12
Coverage (ft ² /gal.)	100-400
H F R Ratings	1-0-1
Substrate Use	All
Other:	Nearly water insoluble after drying Can be used at cryogenic temperatures

Sizes and colors

Product is white:
(will gray-out on first heat up due to small amount of organic binder)

Standard Size: Nalgene quart or gallon

CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.