



120 Valley Court
Oak Ridge, TN 37830
Ph: 865-482-5717
FAX: 865-482-1281
zypcoatings.com

BN Powder Grade ZG

Boron Nitride Powder for Use in Research and Industry

Boron Nitride powder produced by ZYP Coatings' unique-continuous process is ultra-high-purity. The BN powder can be added to many plastics, potting compounds, oils, greases, and other materials to provide enhanced thermal conductivity and dielectric strength. As a dry-powder lubricant, BN powders also give anti-squeak/anti-squeal noise reduction. BN is regularly used to aid forming, reduce sticking, and provide release after molding/casting operations. The uses for BN are unmatched as a ceramic material.

Key Attributes

- Highly Lubricious, Even in Vacuum
- Chemically Inert with High Refractoriness
- High Electrical Resistivity and High Dielectric Strength with Low Dielectric Constant
- High Thermal Conductivity
- Transparent to Microwaves
- Low Thermal Expansion
- Non-Toxic

Ideal Use


- Thermally-Conductive Inert Filler-Additive
- Barrier Layer with Graphite
- Anti-Stick/Anti-Sieze
- Providing Release
- Dry Lubricant

Use Notes

1. Use in well-ventilated area.
2. Powder is "fine": avoid generating dusts.

Safety Information

- Consult SDS before use.
- Avoid breathing of dusts.
- For Industrial use only.



■ B
□ N



10 μm

Scanning Electron Micrograph
Grade ZG

The crystal Structure of Hexagonal Boron Nitride leads to plate-like crystal grains that provide excellent lubrication for BN powders

Specifications for Grade ZG

Boron Nitride Content	over 99.9%
Average Particle Size (micrometers)	6-8
	d10 = 1.4 microns
	d50 (median) = 7.4 microns
	d90 = 11.8 microns
Surface Area by BET (sq.m/g)	3 typical
Tap Density (g/cc)	0.23
Water Soluble Boron Oxide	Below 0.1%
Color	White
Max Use Temperature	Air 1832 F / 1000 C
	Vac 2552 F / 1400 C
	Inert 3272 F / 1800 C
Use Atmosphere	All
H F R Ratings	1-0-0

Sizes and colors

Product is fine white powder.

Standard Size: 1 kilogram bag

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted. .