



120 Valley Court
 Oak Ridge, TN 37830
 Ph: 865-482-5717
 FAX: 865-482-1281
 zypcoatings.com

Comparison of High Temp Water-Based Sealants and Glues

High Temperature Water-Based Sealants and Glues – Comparison of Properties

PRODUCT	VISCOSITY	MAX USE-TEMPERATURE (C)	SUBSTRATES	MAIN USE AREA	APPLICATION
Cera Mastic	Paste/putty	300-1500	Oxide/non-oxide ceramics; metals (T<500 C)	Gluing/joining/repairing; bonding dissimilar materials (metal/ceramics)	Putty knife/trowel
Vitragard FS	3000 centipoises	900	Fused silica (dense/porous); 3D printed ceramic articles	Sealing/bonding	Brush
Supercoat	100-300 centipoises	850	Metals	Sealing	Air spraying
BN Cera Patch	Paste	900-1000	Ceramics	Patching; nonwetting with molten aluminum	Putty knife/trowel
Cera Glue Sealcoat	7000 centipoises	<= 800	Oxide ceramics; BN; 3D printed ceramic articles	Sealing/bonding tiles; calcium silicate parts	Brush
Cera Glue AA	400 centipoises	1500	Alumina/high-Al ₂ O ₃	Bonding/gluing; hermetic sealing	Brush
Cera Glue BondCoat	Thick Paste	1500	ZrO ₂ , SiC, BN	Bonding/joining dense parts	Brush/trowel

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.