



120 Valley Court
Oak Ridge, TN 37830
Ph: 865-482-5717
FAX: 865-482-1281
zypcoatings.com

PlasterMix ZY Casting Powder

Powder Refractory Mixture for Forming Slurry for Plaster-like Casting

PlasterMix ZY is a Yttria-based plaster-forming mixture, which on merely adding water and stirring, becomes like Plaster-of-Paris that can be cast into silicone forms to make "investment" molds or porous shapes or even be applied like stucco to firebrick.

Key Attributes

- Uses Yttrium Oxide as the cementitious phase for forming plaster
- Readily forms slurry with working behavior like Plaster-of-Paris
- Slurry can be cast for forming shapes or "investment" molds
- Provides mixing/working time of over 10 minutes before setting begins and up to an hour before completely setting up as plaster
- Heating to 800-1400 C provides a well-bonded, free-standing shape
- Sandable after drying or firing
- Yields crack-free thick dried or fired pieces
- Water-based, safe and easy to use or cleanup
- Contains no Refractory Ceramic Fiber (RCF), no sulfur, no silica

Ideal Use

- Forming "investment" molds for casting very reactive molten metals
- Providing a stable porous (typically^{1,2} 50-65% porous, with pore diameter 0.5-2 microns) refractory part based on Yttrium Oxide
- Forming a weakly-bonded, highly-stable refractory stucco/plaster on firebrick and porous substrates

Use Notes

1. Add powder to mixing container. Add water and stir until uniform. Note that the slurry will become cool and then somewhat warm and thicken some before thinning back out as time goes over five minutes.
2. Generally at <10 minutes or so, cast the slurry into silicone form/mold as a thin liquid and 'set' for about one hour. Any excess liquid will form on top and can be tamped off with a paper towel during the hour. Continue to "set" for 1-2 more hours.
3. Place into dryer at 60 C overnight, and then remove from the silicone form/mold. Allow to dry further for 1-2 hours.
4. Place into furnace to fire to desired temperature, generally 800 to 1400 C.

Example: 50 grams of powder is mixed with 15 cc of water for forming a slurry to fill a 25 cc silicone form/mold, such as cylinder 4 cm diameter and 2 cm high. After 60 C drying, typical heating rate was 100 C/hr to 600 C, 250 C to 600-1000 C, then 600 C/hr to 1000-1400 C with "soak" of 0.5 hr.

Large parts require slower heating rate to upper temperature (such as 6 C/hr to 650 C, 50 C/hr 650-800 C, 120-600 C/hr 800-1400 C.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.



Specifications

Active Ingredient	Zirconium/Yttrium Oxide*
Max Use Temperature with All Atmospheres	>= 1400 C (2552 F)
Fired Composition	>92% Zr-Y-O
Liquid Carrier	Water
Binder Phase	Proprietary
Specific Gravity	2.0
Color	Cream
Shelf Life (months)	Indefinite ... but avoid getting wet before use
H F R Ratings	1-0-0

*Note: all Yttrium Oxide version available as Plastermix YY Casting Powder; contact ZYP Coatings (not on website).

Sizes and colors

Plastermix ZY is a cream colored powder mixture. Standard Size: 8 oz. or 32 oz. (quart) clear plastic container

Safety Information

- Consult SDS before use.
- For Industrial Use only.

References

1. C. E. Holcombe, Jr., "Sintering of Yttria Binders," American Ceramic Society Bulletin, 57, 693 (1978).
2. C. E. Holcombe, C. C. Edwards, and D. A. Carpenter, "New Yttria Plasters," Report Y-2104, Dept. of Energy, Oak Ridge Y-12 Plant, Oak Ridge, Tennessee (1978).