

120 Valley Court Oak Ridge, TN 37830 Ph: 865-482-5717 FAX: 865-482-1281 zypcoatings.com

**Zypcoat® CZO** 

# **Calcium Zirconate Water-Based Coating**

Zypcoat® CZO is based on a lesser-known mixed oxide – namely Calcium Zirconate or Calcium-Zirconium-Oxide, CaZrO<sub>3</sub>, which has melting point of 2325 C. Zypcoat CZO forms 100% CaZrO<sub>3</sub> on heating over 500 C. It is usable in air atmospheres as well as inert/vacuum to temperatures to >2000 C, while bonding well to all substrates – ceramic, graphite, metal. Due to its high melting point and expected high stability with most materials, Zypcoat CZO is suitable for R&D studies at extreme temperature and conditions.

## **Key Attributes**

- Unique compound of CaO and ZrO<sub>2</sub>
- Very high temperature melting point and use-temperature
- Expected low thermal and electrical conductivity
- Usable in all atmospheres
- Water-based, easy to use and cleanup

### **Ideal Use**

- High-Temperature Ceramics (HTC) research/development
- Testing in extreme environments
- Reactive-molten metal processing
- Barrier coating to prevent interactions

#### **Use Notes**

- 1. Re-suspend if needed. Dilute sparingly with water if desired.
- 2. Clean surfaces to be painted of any oils, dirt, scale, etc.
- 3. Apply a single layer by brush or spray, drying after each layer.
- 4. Allow to thoroughly dry before use.

## **Safety Information**

- · Consult SDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



### **Specifications**

Active Ingredient	$CaZrO_3$
Max Use Temperature	
with All Atmospheres	>2000 C (>3632 F)
Fired Composition	100% CaZrO₃
Liquid Carrier	Water
Binder Phase	CaO-ZrO <sub>2</sub>
Brookfield Viscosity (cps)	2000 @ 3/30
Specific Gravity	2.25
Color	White
Shelf Life (months	>12
Coverage (ft²/gal)	100 to 400
Coating pH	2
H-F-R Ratings	1-0-0
Substrate Use	All
Other Contains no Silicon	Oxide and no Boron

### Sizes and Colors

Zypcoat CZO is a white-colored paint.

Standard Sizes: gallon, quart, or pint Nalgene containers

### CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.