

120 Valley Court Oak Ridge, TN 37830 Ph: 865-482-5717 FAX: 865-482-1281 zypcoatings.com

Enhanced Adherence Solvent-Based Boron Nitride-Silicone Coating

BN SiloxyKote has uniform, tough/adherent bonding to all substrates and in all atmospheres to over 800 C (1472 F).

Key Attributes

- Good Adherence Ambient to 800 C
- Fast Drying, Solvent Based
- No "heat-cure" or primer required
- Ready to use on applying (like housepaint) and drying
- For all substrates/atmospheres
- Dilutable/Cleanable with Acetone and/or Ethanol

Ideal Use

- Reaction-Barrier Layer with Solid or Molten Materials
- Providing Release

Use Notes

- 1. Resuspend if needed.
- 2. Clean surfaces to be painted of any oils, dirt, scale, etc.
- 3. Apply one thin layer by brush, dip or air-spray.
- 4. Allow to dry at room temperature before usegenerally less than 5 minutes. Recoat if desired.

Safety Information

- Consult SDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



Specifications

Active Ingredient		BN/SiO ₂
Max Use Temperatu	ire	> 800 C / > 1472 F
Use Atmosphere		All
Fired Composition		60% BN
Liquid Carrier		Ethanol/Acetone
Binder Phase		Silicone Resin
Brookfield Viscosity	(cps)	300 @ 3/60
Specific Gravity		1.05
Color		White
Shelf Life (months)		>12
Coverage (ft ² /gal)		100-400
H F R Ratings		1-3-0
Substrate Use		All
Other:	Water	r insoluble after drying

Sizes and colors

Product is white: will become gray/brown on first heat up >300 C – returns to white >600 C.

Standard Size: 1 quart or 1 gallon easy-open Curtec container

CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.