

120 Valley Court Oak Ridge, TN 37830 Ph: 865-482-5717 FAX: 865-482-1281 zypcoatings.com

# Yttria CeraCast Powder

## Yttrium Oxide Based Castable Dry Powder Mixture

Yttria CeraCast Powder is a dry Yttrium Oxide (Y<sub>2</sub>O<sub>3</sub>) powder mix which, on adding around 50 wt% water and stirring, can be poured/cast into silicone molds to form parts. After casting and drying, firing the cast part to only 1300 C results in a high-density (typically >= 85%) yttria refractory.

### **Key Attributes**

- Based on highly stable refractory Yttrium Oxide  $(Y_2O_3)$
- Prepared as a slurry from dry mixture by just adding water
- Readily prepared into near full density parts by cast-and-sinter technique or by press-and-sinter
- Low shrinkage during drying
- Low sintering temperature of only 1300 C for obtaining >95% yttrium oxide over 85% dense
- Use temperature >= 1300 C and possibly to 2000 C
- Water-based easy cleanup.

## **Use Notes**

- 1. Mix powder well with water to a uniform consistency. Recommended mixing ratio is 45-55% water with 45-55% powder mix, by weight. Less water can lead to greater density in the final part. Mixing time should be less than five minutes. Vinegar can be used in place of water to increase the green strength of the cast piece.
- 2. After mixing, quickly pour or trowel the suspension into a silicone mold, paper cup, etc. Place the mold on a vibrating table or tamp the mold for a short while to remove bubbles from the suspension.
- 3. Dry at 60 C overnight and then carefully remove the part from the mold.
- 4. Sinter the part by heating to 600 C (rate: 1 C/min) and holding for 0.5-1 hour(s), and then heating to 1300 C (rate: 10 C/min) and holding for 1 hour.

Example 35 g. powder + 16 cc water (or vinegar) casts a 'puck' of 22 cc [1.5" D, 0.7" H].

ALSO: The powder can be pressed with conventional hydraulic press, followed by sintering with the conditions above (step 4).



## Specifications

SEM Image of Sintered 95% Yttria Pellet

Active Ingredients	Yttrium Oxide (Y <sub>2</sub> O <sub>3</sub> )
Max Use Temperature with	
All Atmospheres	>= 1300 C (2372 F)
	possibly to 2000 C (3632 F)
Fired Composition	95% Y <sub>2</sub> O <sub>3</sub>
with special r	nineralizers (sintering aids)
Color	White
Shelf Life (months)	
Indefinite but av	oid getting wet before use
H F R Ratings	1-0-0
Other Notes	Mineralizer ingredients may
be ur	wanted and tend to volatilize
above 130	00 C thus can potentially
lead to a	III-yttria parts/components.

#### Sizes and colors

Yttria CeraCast Powder is white colored powder. Standard Sizes: 1 qt. or 8 oz epoxy-lined can

#### Ideal Use

- · Casting your own specialty refractory shapes
- Producing high-density yttria parts at only 1300 C sintering in any atmosphere
- Making electrically and thermally insulating ceramic shapes

#### **Safety Information**

- Consult SDS before use.
- For industrial use only

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.