



120 Valley Court
 Oak Ridge, TN 37830
 Ph: 865-482-5717
 FAX: 865-482-1281
 zypcoatings.com

JK SD

Solvent-Based, Dippable Boron Nitride Coating for Superplastic Forming Operations

JK SD is a specially formulated solvent-based, very-low-viscosity BN coating to allow dipping onto “blanks” to yield very thin layers that can accommodate the extreme stretching of superplastic forming operations. The uniform-sized BN particles give good adhesion and lubrication over the superplastic-forming and quick-plastic-forming (SPF/QPF) cycle. The consistency of JK SD allows its use for applying thin layers by air-spray as well as dipping.

Key Attributes

- Provides lubrication over the entire SPF-QPF cycle
- Flows with the metal
- Permits easy removal/release after forming
- Minimizes coating build-up on dies
- Ideal for dipping ... OK also for air-spraying
- Solvent-based (Ethanol), Fast-Drying, Flammable

Ideal Use

- Coating metal sheets that are to be SPF-QPF processed
- For any parts that are to be coated by dipping or air-spraying

Use Notes

1. Resuspend if needed. Can dilute with Ethanol or Acetone (for faster drying) ... use for clean up also.
2. Clean surfaces to be painted of any oils dirt, scale, etc.
3. Apply one thin layer by dipping or air-spray
4. Allow to dry before use

Safety Information

- Consult MSDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



Specifications

| | |
|---|---|
| Active Ingredient | BN |
| Max Use Temperature | Air 1832 F / 1000 C Vac 2552 F / 1400 C Inert 3272 F / 1800 C |
| Use Atmosphere | All |
| Fired Composition (Air @700 C) | >95% BN |
| Liquid Carrier | Ethanol |
| Binder Phase | MgSiO _x |
| Brookfield Viscosity (cps) | 15 @1/60 |
| Specific Gravity | 0.87 |
| Color | White |
| Shelf Life (months) | >12 |
| Coverage (ft ² /gal) on Metals | To 400 |
| H F R Ratings | 1-3-0 |
| Substrate Use | All |

Sizes and colors

JK SD is a white colored solvent-based paint.

Standard Size: wide-mouth Nalgene container
 Also available in 5 gallon pail upon request.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.