



120 Valley Court  
 Oak Ridge, TN 37830  
 Ph: 865-482-5717  
 FAX: 865-482-1281  
 zypcoatings.com

**Type E**

## Highest Purity Erbium Oxide (Er<sub>2</sub>O<sub>3</sub>) Water-Based Coating

Type E is a relatively-soft, washcoat-type of Erbium Oxide (Y<sub>2</sub>O<sub>3</sub>) coating which provides a very-high-purity (99.99%) Er<sub>2</sub>O<sub>3</sub> layer that is usable in vacuum and inert atmospheres to 2000 C (3632 F). This coating can be used instead of Type Y (Y<sub>2</sub>O<sub>3</sub>) whenever Yttrium is not desired, yet the properties of Y<sub>2</sub>O<sub>3</sub> are needed. Type E should NOT be used in air atmospheres.

### Key Attributes

- Provides the great properties of Er<sub>2</sub>O<sub>3</sub>, essentially the same as Yttrium Oxide other than density ... low electrical conductivity; low thermal conductivity; high-temperature thermodynamic stability; inert barrier to interactions/reactions
- Applies like housepaint - brush, dip, or spray
- Ideal for highly reactive molten metals
- Safe, Water-Based

### Ideal Use

- Coating Graphite crucibles, molds, and trays
- Anti-stick with brazing
- Barrier for diffusion bonding

### Use Notes

1. Resuspend if needed. Can dilute with water if desired.
2. Clean surfaces to be painted of any oils dirt, scale, etc.
3. Apply 1-3 layers by brush, dip or air-spray - drying after each layer
4. Allow to dry thoroughly before use.

### Safety Information

- Consult SDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



### Specifications

Active Ingredient	Er <sub>2</sub> O <sub>3</sub>
Max Use Temperature	
Inert, Vac (no C)	2000 C (3632 F)
Vac (with C present)	1500 C (2732 F)
Air =	NOT RECOMMENDED
Use Atmosphere	Vacuum or Inert
Fired Composition	>99% Er <sub>2</sub> O <sub>3</sub>
Liquid Carrier	Water
Binder Phase	Cellulosic
Brookfield Viscosity (cps)	650 @2/30
Specific Gravity	1.7
Color	Pink
Shelf Life (months)	>12
Coverage (ft <sup>2</sup> /gal)	100 to 400
Coating pH	7-8
H F R Ratings	1-0-0
Substrate Use	All

### Sizes and colors

Type E is a pink colored paint.

Standard Size: 1 gallon wide-mouth Nalgene  
 1 quart wide-mouth Nalgene

### CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.